

1-1-2006

## A Comparative Microleakage Study of Retrograd Filling Materials

SELÇUK ERKUT

R. CEM TANYEL

NURULLAH KEKLİKOĞLU

SAMİ YILDIRIM

AHMET BÜLENT KATİBOĞLU

Follow this and additional works at: <https://journals.tubitak.gov.tr/medical>



Part of the [Medical Sciences Commons](#)

---

### Recommended Citation

ERKUT, SELÇUK; TANYEL, R. CEM; KEKLİKOĞLU, NURULLAH; YILDIRIM, SAMİ; and KATİBOĞLU, AHMET BÜLENT (2006) "A Comparative Microleakage Study of Retrograd Filling Materials," *Turkish Journal of Medical Sciences*: Vol. 36: No. 2, Article 7. Available at: <https://journals.tubitak.gov.tr/medical/vol36/iss2/7>

This Article is brought to you for free and open access by TÜBİTAK Academic Journals. It has been accepted for inclusion in Turkish Journal of Medical Sciences by an authorized editor of TÜBİTAK Academic Journals. For more information, please contact [academic.publications@tubitak.gov.tr](mailto:academic.publications@tubitak.gov.tr).

## CLINICAL INVESTIGATION

# A Comparative Microleakage Study of Retrograd Filling Materials

Selçuk ERKUT<sup>1</sup>, R. Cem TANYEL<sup>1</sup>, Nurullah KEKLİKOĞLU<sup>2</sup>, Sami YILDIRIM<sup>1</sup>, Ahmet Bülent KATİBOĞLU<sup>1</sup>

<sup>1</sup>Department of Oral Surgery, School of Dentistry, İstanbul University, İstanbul- Turkey

<sup>2</sup>Department of Histology, Faculty of Dentistry, İstanbul University, İstanbul- Turkey

Received: August 23, 2005

**Abstract:** The aim of the retrograde filling in apical resection operation is to obtain an effective and hermetic apical sealing. According to the development of technology many materials are now used in apical resection operations for retrograde fillings. An in vitro dye leakage study was performed to test the sealing ability of IRM, MTA, amalgam and zinc-phosphate cement materials. Forty single rooted extracted human teeth were used in this study. After cleaning and shaping, all the roots were obturated with zinc-phosphate cement and gutta-percha. Teeth were randomly divided into four groups. After root-end resections of the teeth in all groups, 3 mm depth of retrograde class I cavities were performed in 3 groups with micro-handpiece preparations. Retrofillings of each group were performed with IRM, MTA and silver amalgam. Methylene blue was used to determine the apical leakage. After sectioning the roots longitudinally linear dye penetration in denting and cement was measured with a caliper under stereomicroscope and the results were statistically analyzed.

**Key Words:** Retrograde filling, IRM, MTA, amalgam, zinc-phosphate cement

## Introduction

The preferred treatment of failing endodontic cases is non-surgical retreatment and these retreatments usually have successful outcomes. However, because of the complexity of root canal systems, inadequate instrumentation and presence of physical barriers, sometimes achievement is impossible. In these cases surgical endodontic therapy becomes the first alternative (1,2).

Among the possible causes of failure in endodontic surgery, the most frequent is the incomplete cleaning of the root canal and sealing of all communications between the root canal and periradicular tissues (3,4,5). It was pointed out that possible bacterial infiltration through the tubules can take place more frequently in the presence of coronal leakage into the root canal system, (6,7) and leakage tests performed on patients of different ages showed greater leakage in young subjects (8).

The primary goal in apical resection is to perform a hermetic sealing between the apical portion of the root canal and periapical tissues by retrograde root end

filling. By hermetic sealing with a root end filling, prevention of the passage of microorganisms and their products into the periapical tissues can be achieved. (9,10,11) Root end filling materials can be used into a class I cavity after the resection of the root. It should not be forgotten that as the angle of the bevel increases, the apical leakage also increases due to the permeability of the dentinal tubules (12). So the root should be resected as perpendicular to the long axis of the root as possible (13,12). Although at least 2-3 mm of root end removed is recommended in apical resection (14) Philip et al showed in their studies that 2 mm or 4 mm of the apex resection did not show a significant difference in apical dye penetration (15). Root end cavity can be prepared by a bur or an ultrasonic instrument. The researches have demonstrated that ultrasonic instruments create more micro fractures than burs during root end cavity preparations (12). Also the depth of the root end cavity is a significant factor achieving hermetic apical seal. Frank et al demonstrated that 3 mm depth class I cavity for an amalgam root end filling reduced apical leakage (16,17,18,19).

With an ideal material, the apical portion of the canal can be sealed from the surrounding tissues to prevent bacterial migration (20,11). The improvements of technology provide the opportunity of testing many materials and selecting the best retrograde filling material. It has been suggested that the ideal retrograde filling material should be non-toxic, non-carcinogenic, biocompatible and should prevent leakage of microorganisms to the apical tissues. Sealing ability of materials should not change due to the tissue fluids or the moisture in the environment. Also materials should be easy to manipulate and be radioopaque in order to be recognized (13).

Numerous materials have been suggested as root end filling materials: gutta-percha, amalgam, polycarboxylate cement, zinc phosphate cement, zinc oxide eugenol paste, IRM cement, Eba cement, Cavit, Glass ionomers, composite resins and other materials such as gold foil and leaf, silver points, cyanoacrylates, polyhema and hydron, diaket root canal sealer, titanium rews and teflons (11,13,15,16,21-23).

The aim of this study was to compare the sealing ability of zinc-phosphate cement and gutta-percha, amalgam, IRM (intermediate restorative material) cement and MTA (mineral trioxide aggregate) with each other.

## Materials and Methods

Forty extracted single rooted human upper incisors and canines were used in this study. Root lengths were at least 11-12 mm and these with no evidence of previous root canal therapy of teeth were selected. Teeth were collected and stored in 10% formalin. X-rays were taken to assess the absence of anatomical anomalies in the canal system. After an ultrasonic cleaning for the remnants and calculus remaining, endodontic treatment beginning from 15 K-type file up to 45 K-type file was performed at a working length of 1mm shorter from the apical foramen. 5.5% solution of NaOCl was used as an irrigant. All roots were sectioned 3 mm from the apex at an angle of 90° with a micro reciprocating saw (Ref:5100-37 TPS) under water irrigation (15). All canals were dried with paper points and filled with zinc-phosphate cement (Adhesor, Spofa Dental) and gutta-percha points. Teeth were randomly divided into four groups, with ten teeth in each group. Retrograde preparation of 3mm length cavities drilled with a reverse-conic bur (no: 6, acurata) were mounted on a contra-angle high speed hand piece in first three group. Retrograde

cavities of the first group were filled with IRM. IRM was prepared by a microspatula and was treated to teeth with a micropacker. Amalgam was used as a retrograd filling material in the second group. Amalgam was treated to cavities with a microspatula and brinsuar. Third group's retrograde cavities were filled with MTA. The filling materials were prepared according to manufacturers recommendations. The fourth group was left untreated with zinc-phosphate cement and gutta-percha filled root canals.

After retrograde root filling procedures were completed, teeth were coated with three layers of nail varnish except for the apical portion. Then teeth were allowed to dry for 30 minutes. After the drying period, teeth were placed into four tubes containing 1% methylene blue solution for 48 hours.

After 48 hours, teeth were rinsed under running water for 5 minutes and allowed to dry. The roots were divided into two equal halves along the long axis with a micro reciprocating saw (Ref: 5100-37 TPS). The sections were observed under a stereomicroscope at 1,6 X 10 magnification (Leica MS5 Switzerland) and the linear depth of dye penetration was measured on both sides of the retrograde filling material in all sectioned roots of all groups with caliper (Vernier Caliper 200xmm) One Way ANOVA analysis of variance followed by the Dunnett T<sub>3</sub> test for individual contrasts was used to compare the dye penetration.

## Results

Dentinal and apical dye penetration was observed by the stereomicroscope. Dentinal and apical dye penetration in the four groups are seen in Figure (1-4). Figure 1 demonstrates dye penetration of amalgam, Figure 2 MTA, Figure 3 IRM, Figure 4 zinc-phosphate cement fillings. The mean linear measurement values for apical dye penetration of the specimens in each group are shown in Table 1. The mean differences and the significance of values between groups are shown in Table 2. The test specimens which received reverse MTA fillings showed the least leakage but showed no significant difference between reverse amalgam fillings ( $p = 0,221$ ). The specimens which received reverse IRM fillings showed significantly more dye penetration than the reverse amalgam ( $p = 0,022$ ) and MTA fillings ( $p = 0,0005$ ) There was no significant difference between the specimens received reverse IRM fillings and zinc-phosphate cement fillings ( $p = 0,123$ ).



Figure 1. Dye penetration of amalgam filling.



Figure 2. Dye penetration of MTA filling.

## Discussion

The primary aim of root canal treatment is the elimination and future exclusion of all microorganisms from the root canal system. Conventional root canal treatment is the preferred treatment to achieve this aim. However, if conventional root canal treatment is

impossible or has failed, an alternative approach will be necessary. Periapical surgery which entails apicotomy and retrograde root filling may be performed. A retrograde root filling is placed to establish an "apical seal" to prevent the passage of microorganisms or their products into periapical tissues. 'Apical seal' is the single and most



Figure 3. Dye penetration of IRM filling.



Figure 4. Dye penetration of zinc-phosphate cement filling.

important factor in achieving success in surgical endodontics (18,24-28).

The most commonly used retrograd root filling material is amalgam but it does not provide a satisfactory seal and there are numerous disadvantages with this material (29-33). In the quest for an effective apical

barrier various techniques and materials have been investigated (21,29-33). There is a long history of using leakage studies to asses the suitability of potential root-end filling materials. There is no standardized leakage test to evaluate the sealing ability of endodontic materials (21). Despite criticism, dye leakage tests still remain the

Table 1. Showing the mean linear measurement values for apical dye penetration of the specimens in each group.

Group	Mean Std.	Deviation	N
1	2.4150	1.2579	20
2	1.3125	0.9716	20
3	0.7650	0.6341	20
4	1.6550	0.6316	20
Total	1.5369	1.0782	20

F = 11.47; P = 0.0005

One way ANOVA

Table 2. Showing the mean differences and the significance of values between groups.

Multiple comparisons						
GROUP	(I)	GROUP (J)	Mean Difference (I-J)	Std. Error	Sig.	
Dunnett T3	1	2	1.1025	0.2884	.022	
		3	1.6500	0.2884	0.0005	
		4	0.7600	0.2884	0.123	
	2	1	-1.1025*	0.2884	0.022	
		3	0.5475	0.2884	0.221	
		4	-0.3425	0.2884	0.710	
	3	1	-1.6500*	0.2884	0.0005	
		2	-0.5475	0.2884	0.221	
		4	-0.8900*	0.2884	0.0005	
	4	1	-0.7600	0.2884	0.123	
		2	0.3425	0.2884	0.710	
		3	0.8900*	0.2884	0.0005	

best test for screening adaptation and sealing ability and it is stated that dyes are simpler, cheaper, safer and easier to handle than radioisotopes (13,21,34). The use of dyes is one of the oldest and commonest methods of studying microleakage. (21,35-48) A variety of dyes have been used; these include indian ink, erythrosine B solution, aqueous solution of fuchsin, fluorescent solution, methylene blue solutions and others (37-43).

Kersten and Moorer (49), found that leakage of the commonly used dye methylene blue was comparable with that of a small bacterial metabolic product of similar molecular size.

Higa et al (50), evaluated the influence of storage time (0 versus 24 hours) on the amount of dye leakage of amalgam, super EBA, or IRM and their results showed that storage time had no significant influence on the amount of dye leakage. It was concluded that 3 mm deep retrograde cavities or cavities extended coronally into the root canal at least to the height of the bevel significantly reduced the apical leakage (15,16,18,25). So we prepared 3 mm depth of apical cavities in our study. Methylene blue dye was chosen for this study not just because it is the most commonly used but because it exhibits a sensitivity surpassing even that of radioactive isotopes.

It has been demonstrated that as the angle of the bevel increases the apical leakage also increases due to the greater apical surface and greater number of dental tubules and its permeability (3,13,52). So we resected all root ends as perpendicular to the long axis of the root as possible.

Higa et al (50), Abdal and Retief (43), Smee et al (27) and Bondra et al (28), showed that IRM provided a better seal than amalgam or super EBA. In a similar study Stabholtz et al (53), found that Restodent sealed significantly better than zinc phosphate cement, cavitation, durclon and amalgam. According to their investigation amalgam was significantly inferior to the four other materials and in addition they showed that zinc phosphate did not differ significantly from cavitation or durclon.

In a clinical retrospective study, Dorn and Gartner (31), examined the success rate of EBA, IRM, zinc free high copper amalgam and found super EBA and IRM had significantly higher success rate than amalgam.

Sealing ability of MTA was superior to that of amalgam or Super EBA in different dye and bacterial leakage methods (40,54). Setting time of MTA was much longer than amalgam or IRM and marginal adaptation was better than amalgam and IRM (55).

In our study, reverse MTA filling showed the least leakage but the difference between amalgam and MTA was not significant. Dye penetration was significantly more in IRM fillings and zinc phosphate cement than MTA and amalgam. There was no significant difference between the specimens that received reverse IRM fillings and zinc phosphate cement fillings. These results corroborate with previous findings that show MTA seals significantly better than amalgam and IRM. Dye penetrations in MTA placed cavities were less than that of

others. This is probably due to its superior marginal sealing ability.

Comparison of the data obtained from various leakage studies shows considerable variation in the results of these investigations, and examination of clinical studies shows that there are many variables in these investigations. The main variables include: the number of cases, materials tested, different procedures, techniques and different kind of dyes, lack of standardization or evaluation criteria for quantitative results obtained in these studies. Because of these variables it is difficult to compare the results with one another.

The majority of leakage studies have been performed in vitro with little or no similarities to in vivo conditions. One of their major limitations is the amount of fluid exchange between the apical root canal walls and the root end filling material. On the other hand the purpose of placing a root end filling material is to prevent penetration of irritants from the root canal system into periradicular tissues. Thus coronal seal of root end filling material is probably more important than that of the apical seal.

As a result despite their popularity and ease of use the results and clinical significance of leakage studies have been questioned.

*Corresponding author:*

*Selçuk ERKUT*

*Zuhuratbaba Cad. Kubilay Sok.*

*Elmas Apt. No: 14 / 16 D: 21*

*34740 Bakırköy, İstanbul - TURKEY*

*E-mail: selcukerkut@hotmail.com*

**References**

1. O'Conner RP, Hutter JW, Roahen JO. Leakage of amalgam and Super-Eba root-end fillings using two preparation techniques and surgical microscopy. *J Endod* 21: 74-8, 1995.
2. Ingle I, Taintor J. *Endodontics*. 3rd ed. Philadelphia: Lea & Febiger 27-50, 1985.
3. Tidmarsh JO, Arrowsmith MG. Dentinal tubules at the root ends of apicect teeth: a scanning electron microscope study. *Int Endod J* 1989;22:184-9
4. Ingle JI, Beveridge EE, Glick DH, Weichmann JA. Modern endodontic therapy. In: Ingle JI, Backland LK, eds. *Endodontics*. 4th ed. Philadelphia: Lee & Febiger 33, 1994.
5. Harferty FJ, Parkins BJ, Wengraf AM. Success rate in root canal therapy: a retrospective study of conventional cases. *Br Dent J* 28: 65-70, 1970.
6. Gutmann JL, Pitt Ford TR. Management of the resected root end: a clinical review. *Int Endod J* 71: 603-11, 1993.
7. Grossman LI. *Endodontic practice*. 10th ed. Philadelphia: Lea & Febiger 351, 1981.

8. Ichesco WR, Ellison RL, Corcoran JF et al. A spectrophotometric analysis of dentinal leakage in the resected root. *J Endodon* 17: 503-7, 1991.
9. Massimo G, Silvio T, Raffaella M. Ultrasonic root-end preparation: influence of cutting angle on the apical seal. *J of Endod* 24: 726-30, 1998.
10. Dalal MB, Gohil KS. Comparison of silver amalgam, glass ionomer cement and gutta-percha as retrofilling materials: an in vivo and in vitro study. *J Indian Dent Assoc* 55: 153-8, 1983.
11. Chong BS, Pitt Ford TR, Watson TF et al. Sealing ability of potential retrograde root filling materials. *Endod Dent Traumatol* 11: 264-269, 1995.
12. Gilheany PA, Fidgor D, Tyas M. Apical dentine permeability and microleakage associated with root-end resection and retrograde filling. *J Endod* 20: 22-6, 1994.
13. Torabinejad M, Pitt Ford TR. Root end filling materials: a review. *Endod Dent Traumatol* 12: 161-178, 1996.
14. Ingle JI, Cummings RR, Frank AL et al. Endodontic surgery. In: Ingle JI, Bakland LK, eds. *Endodontics*. Baltimore: Lee & Febiger 723, 1994.
15. Philip SB, Bamiduro RO. Effect of apical resection and reverse fillings on thermafil root canal obturations. *J of Endod* 16: 227-29, 1990.
16. Frank JV, Richard GB. Apical leakage associated with retrofilling techniques: a dye study. *J of Endod* 12: 331-36, 1986.
17. Weine FS. *Endodontic therapy*. 3rd ed. St. Louis: CV Mosby Co., 455, 1982.
18. Mattison GD, Von Fraunhofer JA, Delivanis PD, Anderson AN. Microleakage of retrograde amalgams. *J Endod* 11: 340-5, 1985.
19. Arens DE, Adams WR, DeCastro RA. *Endodontic surgery*. Philadelphia: Harper and Row, 159, 1981.
20. William LK, David PA, Harold G. A comparative bacterial microleakage study of retrofilling materials. *J of Endod* 8: 355-8, 1982.
21. Gutmann JL, Harrison JW. *Surgical endodontics*. Boston : Blackwell Scientific Publications, 230-63, 1991.
22. Gary MH, Thom CD. Leakage of amalgam, composite, and super-EBA, compared with a new retrofill material: bone cement. *J of Endod* 1: 29-31, 2000.
23. Dennis LS, Ronald WA, David HP. An evaluation of the effect of methylene blue dye pH on apical leakage. *J of Endod* 9: 435-439, 1993.
24. Harfity FJ, Parkins BJ, Wengraf AM. Success rate of apicectomy. A retrospective study of 1,016 cases. *Br Dent J* 129: 407-13, 1970.
25. Beatty R. The effect of reverse filling preparation design on apical leakage. *J Dent Res* 65: 259, 1986.
26. Ingle JI, Glick DH. *Modern endodontic therapy*. In: Ingle JI, 1st ed. Philadelphia: Lee & Febiger, 54-777, 1965.
27. Smee G, Bolanos OR, Morse DR et al. A comparative leakage study of P-30 resin-bonded ceramic, Teflon, amalgam and IRM as retrofilling seals. *J Endod* 13: 117-21, 1987.
28. Bondra DL, Hartwell GR, MacPherson MG et al. Leakage in vitro with IRM, high copper amalgam and EBA cement as retrofilling materials. *J Endod* 15: 122-4, 1989.
29. Friedman S. Retrograde approaches in endodontic therapy. *Endod Dent Traumatol* 7: 97-107, 1991.
30. Chong BS, Pitt Ford TR, Watson TF. The adaptation and sealing ability of light-cured glass ionomer retrograde root fillings. *Int Endod J* 24: 223-33, 1991.
31. Dorn SO, Gartner AH. Retrograde filling materials: A retrospective success/failure study of amalgam, EBA and IRM. *J Endod* 16: 391-3, 1990.
32. Chong BS, Pitt Ford TR, Watson TF. Light-cured glass ionomer as a retrograde root seal. *Int Endod J* 26: 218-24, 1993.
33. Chong BS, Owadally ID, Pitt Ford TR et al. Cytotoxicity of potential retrograde root filling materials. *Endod Dent Traumatol* 10: 129-33, 1994.
34. MacNeil K, Beatty R. Ketac silver and Fiji II as reverse fillings: a dye study. *J Dent Res* 66: 297, 1987.
35. Spanber L, Aciero T, Cha BY. Influence of entrapped air on the accuracy of leakage study using dye penetration method. *J Endod* 15: 548-51, 1989.
36. Özata F, Erdilek N, Teza H. A comparative sealability study of different retrofilling materials. *Int Endod J* 26: 241-245, 1993.
37. Sidhu SK. Sealing effectiveness of light cured ionomer cement liners. *J Prothet Dent* 68: 891-894, 1992.
38. Olson AK, McPherson MG, Hartwell GR et al. An in vitro evaluation of injectable thermoplasticized guttapercha, glass ionomer and amalgam when used as retrofilling materials. *J Endod* 16: 361-364, 1990.
39. Bondra DL, Hatwell GR, McPherson MG et al. Leakage in vitro with IRM, high copper amalgam and EBA cement as retrofilling materials. *J Endod* 15: 157-160, 1989.
40. Torabinejad M, Watson TF, Ford TR. Sealing ability of a mineral trioxide aggregate when used as a root end filling material. *J Endod* 19: 591-595, 1993.
41. Alhadainy HA, Himel VT. Evaluation of the sealing ability of amalgam, cavit and glass ionomer cement in the repair of furcation perforations. *Oral Surg Oral Med Oral Pathol* 75: 362-366, 1993.
42. Negm MM. The effect of varnish and pit and fissure sealants on the sealing capacity of retrofilling techniques. *Oral Surg Oral Med Oral Pathol* 66: 483-488, 1988.
43. Abdal AK, Retief DH, Jamison HC. The apical seal via the retrosurgical approach. II. An evaluation of retrofilling materials. *Oral Surg* 54: 213-218, 1982.



44. Schwarts SA, Alexander JB. A comparison of leakage between silver glass ionomer cement and amalgam retro fillings. *J Endod* 14: 385-391, 1988.
45. Pissiotis E, Sapounas G, Spanberg LSW. Silver glass ionomer cement as a retrograde filling material: a study in vitro. *J Endod* 17: 225-229, 1991.
46. Stabholz A, Khayat A, Ravanshad SH et al. Effects of ND:YAG laser on apical seal of teeth after apicectomy and retrofill. *J Endod* 18: 371-375, 1992.
47. Tuggle ST, Anderson RW, Pantera EA et al. A dye penetration study of retrofilling materials. *J Endod* 15: 122-124, 1989.
48. Starkey DL, Anderson RW, Pashley DH. An evaluation of the effect of methylene blue dye pH on apical leakage. *J Endod* 19: 435-439, 1993.
49. Kersten HW, Morer WR. Particles and molecules in endodontic leakage. *Int Endod J* 22: 118-124, 1989.
50. Higa RK, Torabinejad M, Mc Kendry DJ et al. The effect of storage time on the degree of dye leakage of root end filling materials. *Int Endod J* 27: 252-256, 1994.
51. Matloff IR, Jensen JR, Siger L et al. A comparison of methods used in root canal sealability studies. *Oral Surg Oral Med Oral Pathol* 53: 203-208, 1985.
52. Tanzilli JP, Donald R, Moodnik RM. A comparison of the marginal adaptation of retrograde techniques; a scanning electron microscope study. *Oral Surg Oral Med Oral Pathol* 50: 74-80, 1980.
53. Stabholtz A, Shani J, Friedman S et al. Marginal adaptation of retrograde fillings and its correlation with sealability. *J Endod* 5: 218-23, 1985.
54. Torabinejad M, Falah R, Kettering JD et al. Bacterial leakage of mineral trioxide aggregate as a root end filling material. *J Endod* 21: 109-21, 1995.
55. Torabinejad M, Wilder Smith P, Pittford TR. Comparative investigation of marginal adaptation of mineral trioxide aggregate and other commonly used root end filling materials. *J Endod* 1995; 21: 295-299